

Сертификат анализа

XL2-77855

Reading No 452
 Mode General Metals
 Time 2014-07-16 08:18
 Duration 49.06
 Units %
 Sigma Value 2
 Sequence Final
 Alloy1 C857YelBs : 0.58
 Alloy2 No Match : *2.78
 Flags ModCF Set 3
 SAMPLE
 HEAT
 LOT
 BATCH
 MISC
 NOTE

| Наименование | % | ± | Error |
|--------------|--------|---|-------|
| Sb | 0 | | N/A |
| Sn | 0.517 | ± | 0.020 |
| Cd | 0 | | N/A |
| Pd | 0 | | N/A |
| Ag | 0 | | N/A |
| Ru | 0 | | N/A |
| Mo | 0 | | N/A |
| Nb | 0 | | N/A |
| Zr | 0 | | N/A |
| Bi | 0 | | N/A |
| Pb | 1.423 | ± | 0.048 |
| Se | 0 | | N/A |
| Au | 0 | | N/A |
| W | 0 | | N/A |
| Zn | 33.460 | ± | 0.172 |
| Cu | 62.919 | ± | 0.248 |
| Ni | 0.297 | ± | 0.017 |
| Co | 0 | | N/A |
| Fe | 0.477 | ± | 0.020 |
| Mn | 0.125 | ± | 0.016 |
| Cr | 0 | | N/A |
| V | 0 | | N/A |
| Ti | 0 | | N/A |
| Al | 0 | | N/A |
| S | 0 | | N/A |
| P | 0 | | N/A |
| Si | 0.387 | ± | 0.056 |
| Mg | 0 | | N/A |

Исполнитель _____

Ответственный _____